



**Notes:**

1. All dimensions are in millimetres unless shown otherwise.
2. Resurfacing will generally be over a full or half lane width but small areas of resurfacing may be included within an overall works order for resurfacing.
3. Where the excavation is below surface course level the edges of the various construction layers shall be stepped back 100 as indicated.
4. When a cavity is excavated the sides of the cavity shall be painted with 160/200 pen bitumen and the base of the cavity shall be painted with bitumen emulsion class K1-40 spread at a rate of between 0.4 to 0.5 litres per sq.m.
5. For further information refer to Standard Details Guidance Note drawing no. HSD/100/001.

DRAWING TITLE:  
**Series 700: Road Pavements General - Excavation and Reinstatement  
of Existing Flexible Pavements**

SCALE: NTS

DRAWN      CHECKED

INITIALS:      CS      MS

DATE:      12/01/2024      12/01/2024

REV	AMENDMENTS	DRN	CHK'D	DATE

DRAWING NO:

**HSD/700/205**

